



CTI-300

oligomer · monomer · photoinitiator· additive

Disclaimer

All products in the text marked with are trademarks of the U-sunny .The information on product specifications provided herein is only binding to the extent confirmed by U-sunny in a written Sales Agreement. U-sunny expressly disclaims any responsibility for the suitability of the products for any specific or particular purposes intended by the user .Suggestions or the use and application of the products and guide formulations are given for information purposes only and without commitment. Such suggestions do not release U-sunny customers from testing the products as to their suitability for the customers intended processes and purposes. U-sunny does not assume any liability or risk involved in the use of its products as the conditions of use are beyond its control. The user of the products is solely responsible for compliance with all laws and regulations applying to the use of the products。 including intellectual property rights of third parties.

CTI-300 Cationic Thermal Initiator

MW: 295

Density,g/cm³: 1.360

Curing condition : 70-150°C 3-15min

Form: White powder

Viscosity at 25°C (50%inPC) : 260cps

CTI-300 is a closed iodonium antimonate cationic initiator with low deblocking temperature, high solubility and high curing reaction activity for epoxy compounds. It can be used as an effective supplement to photocuring initiators. In the electronic packaging, 3D printing, epoxy composite molding and other industries, it is used as a cross-linking agent for post-curing reactions to make the final curing of the main resin more complete, the cured film does not turn yellow, and there is no free acid residue.